



HISTERM EPS 150

Dicke (mm)	Platten in der Packung (Stückzahl)	Packungsmenge (m ²)	Wärmeleitfähigkeit (W/mK)	Wärmewiderstand (m ² K/W)
10	50	25	0,036	0,28
20	25	12,5		0,56
30	16	8		0,83
40	12	6		1,11
50	10	5		1,39
60	8	4		1,67
70	7	3,5		1,94
80	6	3		2,22
90	5	2,5		2,50
100	5	2,5		2,78
110	4	2		3,06
120	4	2		3,33
130	3	1,5		3,61
140	3	1,5		3,89
150	3	1,5		4,17

Plattenabmessungen: 1000 x 500 mm

EPS-EN 13163-T2-L3-W3-S5-P5-BS200-DS(N)5-WL(T)3-CS(10)150