



HISTERM EPS F GRAPHIT

Dicke (mm)	Platten in der Packung (Stückzahl)	Packungsmenge (m ²)	Wärmeleitfähigkeit (W/mK)	Wärmewiderstand (m ² K/W)
10	50	25	0,034	0,31
20	25	12,5		0,63
30	16	8		0,94
40	12	6		1,25
50	10	5		1,56
60	8	4		1,88
70	7	3,5		2,19
80	6	3		2,50
90	5	2,5		2,81
100	5	2,5		3,13
110	4	2		3,44
120	4	2		3,75
130	3	1,5		4,06
140	3	1,5		4,38
150	3	1,5		4,69

Plattenabmessungen: 1000 x 500 mm

EPSEN13163-T1-L2-W2-S2-P5-DS(70,-)1-DS(N)2-WL(T)2-TR100