



HISTERM EPS F

Dicke (mm)	Platten in der Packung (Stückzahl)	Packungsmenge (m ²)	Wärmeleitfähigkeit (W/mK)	Wärmewiderstand (m ² K/W)
10	50	25	0,040	0,25
20	25	12,5		0,50
30	16	8		0,75
40	12	6		1,00
50	10	5		1,25
60	8	4		1,50
70	7	3,5		1,75
80	6	3		2,00
90	5	2,5		2,25
100	5	2,5		2,50
110	4	2		2,75
120	4	2		3,00
130	3	1,5		3,25
140	3	1,5		3,50
150	3	1,5		3,75

Plattenabmessungen: 1000 x 500 mm

EPS - EN 13163T1-L2-W2-S2-P5-DS(N)2-DS(70,-)1-WL(T)2-TR100